

## H44/10/1 HEAT RESISTING HIGH TEMPERATURE GLOSS BLACK

#### Features:

A relatively inexpensive gloss black which is suitable for direct application to mild steel and is heat resistant up to 200°C. Exterior exposure will lead to a loss of gloss after 4 - 6 weeks.

# Availability:

5.0 and 2.5 Litre containers. Please note our products are made to order and it may take 5-7 days before shipping.

#### Volume Solids:

 $55\% \pm 3\%$  (BS 3900 Part A10).

#### Preparation:

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease.

#### Application:

Do not apply to heated surfaces, cool before applying by brush or conventional spray. A minimum of two coats should be applied. Supplied ready for use. Use White Spirit for cleaning.

### Coverage:

Approximately 50 sq metres per 5.0 Litres @ 35 microns dry film thickness.

## Drying:

Touch dry: 2 hours @ 20°C. Hard dry & recoatable: 16 hour @ 20°C.

Health & Safety: Please see MSDS sheet 10019.

**Note:** For internal work, maximum ventilation is required. To assist drying if the air flow is insufficient, fans or other mechanical methods of circulating air should be adopted. Precautions must be taken to prevent operators from inhaling the vapours during application.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control. See Standard Conditions of Sale.

The majority of our products are for professional and trade/contractor use only and are not intended for DIY application. Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.

H44101 04 14

# FOR PROFESSIONAL USE ONLY. READ DATA BEFORE USE.