

HP45/20/4 MEDIUM TEMPERATURE ANTI-CORROSIVE RED OXIDE PRIMER

Features:

A specially formulated primer, resistant to temperatures up to 350°C. Suitable for interior or exterior use, this product is ideal for application to flues, boilers and ovens. Can be over-coated with Technical Paint Services heat resistant finishes.

Availability:

5 and 2.5 Litre containers. Please note our products are made to order and it may take 5-7 days before shipping.

Volume Solids:

 $55\% \pm 3\%$ (BS 3900 Part A10).

Preparation:

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease. It is suitable for direct application to steel surfaces.

Application:

Do not apply to heated surfaces, cool before applying by brush or conventional spray. Thin up to 20% by volume using UTR112 Universal Synthetic Thinners to achieve a suitable spraying viscosity.

Coverage:

Approximately 30 - 40 sq metres per 5 Litres @ 25 microns dry film thickness.

Drying:

Touch dry: 30 minutes @ 20°C. Hard dry & recoatable: 4 hours @ 20°C.

Health & Safety: Please see MSDS sheet 10019.

Note: For internal work, maximum ventilation is required. To assist drying if the air flow is insufficient, fans or other mechanical methods of circulating air should be adopted. Precautions must be taken to prevent operators from inhaling the vapours during application.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control. See Standard Conditions of Sale.

The majority of our products are for professional and trade/contractor use only and are not intended for DIY application. Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.

HP45204 04 14

FOR PROFESSIONAL USE ONLY. READ DATA BEFORE USE.